

## OVERVIEW TECHNICAL DATA

# DOTEC<sup>®</sup> 200

<b>Product description</b>	Engineered composite material made of resin-bound glass fibers and fillers
<b>Standard colour</b>	brown
<b>Main applications</b>	Thermal insulation parts for machine engineering and process industry - compression molded parts -
<b>Delivery program</b>	Sheets, panels and highly precise machined parts and finished components

## Physical characteristics

Properties	Test Standard	Unit	Typical value
Specific density	ISO 1183	g/cm <sup>3</sup>	2
Water absorption	ISO 62	%	0,1

## Thermal characteristics

Properties	Test Standard	Unit	Typical value
Operating temperature, continuous	-	°C	200
Operation temperature, short-term	-	°C	220
Coeff. of linear thermal expansion	DIN 51045	10 <sup>-6</sup> x K <sup>-1</sup>	13
Thermal conductivity	DIN 52612	W/mK	0,3

## Mechanical characteristics

Properties	Test Standard	Unit	Typical value
Compressive strength at 23 °C	ISO 604	N/mm <sup>2</sup>	330
Compressive strength at 200 °C	ISO 604	N/mm <sup>2</sup>	140
Flexural strength at 23 °C	ISO 178	N/mm <sup>2</sup>	100
Modul of elasticity	ISO 178	N/mm <sup>2</sup>	20000

Issue: 11/2014

The standard values shown in this data sheet are measured by standard test methods. Depending on operation terms and dimensions the material properties can differ from these values.

Please contact our applications and sales engineers to clarify the suitability of the material for your application.